

# QUALITY PERFORMS.



## **LANXESS Bromine Solutions**

Brominated polymeric flame retardant  
for polystyrene foams

**X** Emerald Innovation<sup>®</sup> 3000

**QUALITY WORKS.**

**LANXESS**  
Energizing Chemistry

# A GLOBAL LEADER IN FLAME RETARDANTS

## INNOVATIVE. RELIABLE. SUSTAINABLE.

For close to a century, we have helped our customers to meet their needs with a broad portfolio of products and solutions. We are proud of our history, and look forward to helping our customers meet future performance, safety and compliance requirements by refining and redefining our portfolio with new and improved products that maximize sustainability. LANXESS Bromine Solutions is dedicated to providing products that are innovative, reliable and also minimize the impact on our environment and human health without sacrificing performance or quality.

### Sustainable, innovative, high-performance, brominated polymeric flame retardant for polystyrene foams

**Emerald Innovation® 3000**<sup>1</sup> is a highly effective, sustainable brominated polymeric flame retardant offering a variety of enhanced performance properties. This innovative flame retardant is an excellent replacement for Hexabromocyclododecane (HBCD) in both expanded polystyrene (EPS) and extruded polystyrene (XPS) foam products.



### Emerald Innovation® 3000 offers many advantages

- It is a stable, high-molecular weight polymer
- Its polymeric structure makes it not readily bioavailable, thus reducing the environmental concerns that threaten the sustainability of other commercially available brominated flame retardants for polystyrene foams
- It is a comparable alternative to HBCD in EPS and XPS foams, requiring minimal reformulation to use in existing production lines
- Can be used with FR synergist that are commonly used today in EPS/XPS applications
- Its reduced tendency to retain water helps to decrease the residual water content of EPS beads, providing improved process efficiency
- Enables formulators to achieve applicable fire safety standards for polystyrene foam insulation. In pilot plant scale trials in XPS, **Emerald Innovation® 3000** successfully passed the EN ISO 11925-2 and German DIN 4102 B2 flammability tests.
- Provides comparable fire performance<sup>2</sup> in polystyrene foam to foam containing HBCD at equivalent bromine levels.


<sup>1</sup> Emerald Innovation® 3000 is based on technology licensed from DuPont.

<sup>2</sup> Like HBCD, Emerald Innovation® 3000 will need to be stabilized for use in higher temperature processing conditions such as XPS foam applications

## Physical characteristics


Physical form:	Compacted white powder
Bromine content:	~64 %
Softening point:	120 °C
Molecular weight:	100,000–160,000 g/mol
TGA 5% wt loss:	255 °C

## Limiting oxygen index (LOI)



LOI of XPS foam with Emerald Innovation® 3000 equivalent to HBCD at same bromine content

## Flammability performance



Contact us today to learn more about Emerald Innovation® 3000, a cost-effective, performance alternative to HBCD for use in polystyrene foams.



LANXESS Deutschland GmbH  
Business Unit Polymer Additives  
Kennedyplatz 1  
50569 Cologne, Germany

LANXESS Corporation  
Business Unit Polymer Additives  
111 RIDC Park West Drive  
Pittsburgh, PA 15275-1112  
USA  
Phone: +1 412-809-1000

[polymer.additives@lanxess.com](mailto:polymer.additives@lanxess.com)  
<http://flameretardants.lanxess.com>

This information and our technical advice – whether verbal, in writing or by way of trials – is subject to change without notice and given in good faith but without warranty or guarantee, express or implied, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Unless specified to the contrary, the values given have been established on standardized test specimens. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that the results refer exclusively to the specimens tested. Under certain conditions, the test results established can be affected to a considerable extent by the processing conditions and manufacturing process.

©2020 LANXESS.  
Emerald Innovation®, LANXESS and the LANXESS Logo are trademarks of LANXESS Deutschland GmbH or its affiliates. All trademarks are registered in many countries in the world.